

Billerud Pure Performance LINER

Product Description

Pure Performance is produced from 100% virgin fibres. The characteristics for this grade are high and consistent quality combined with superior runnability.

Grammages

135, 160, 175, 200 g/m²

Approvals

Pure Performance is produced in compliance with FDA and BfR packaging norms.

Certification

Production is certified in accordance with ISO 9001, ISO 14001, ISO 50001 and FSSC 22000.

Property	Unit						Method
Grammage	g/m ²		135	160	175	200	ISO 536
Caliper	µm		165	195	215	240	ISO 534
Air resistance	s		80	90	100	100	ISO 5636-5
Scott Bond	J/m ²		350	350	350	350	TAPPI T569
Burst strenght	kPa		640	770	850	970	ISO 2758
SCT	CD	kN/m	3,1	3,6	4,0	4,5	ISO 9895
Tensile	MD	kN/m	1400	1550	1700	1850	ISO 1924
	CD	kN/m	500	650	700	750	
Roughness	PS	ml/min	290	350	370	400	ISO 8791-2
Brightness	PS	%	75	75	75	75	ISO 2470
Cobb	PS	g/m ²	26	26	26	26	ISO 535
	RS	g/m ²	40	40	40	40	
Moisture		%	8,0	8,0	8,0	8,0	ISO 287

MD = Machine Direction CD = Cross Direction PS = Print Side RS = Reverse Side Test climate: 50% RH, 23°C

The table shows typical data for a range of grammages.

Rev. 202205