



Date: January 18, 2019

SteriKraft G WHITE MG KRAFT PAPER

Production Unit: Skärblacka

End uses

SteriKraft G is a bleached wet strength paper with excellent bacterial barrier properties, suitable as a top web for direct heat sealing to various plastic films. SteriKraft G has industry standard functionality for high volume single use medical devices as syringes and IV kits.

Grammages

60 and 70 gsm

Materials

SteriKraft G is produced from pure bleached pulp and consists entirely of primary fibers. The long and strong fibres, from the forests of the Nordic region, give the paper its inherent strength.

Sterilization Method

The packed product can be sterilized by treatment with ETO or irradiation sterilization.

Approvals

SteriKraft G is produced in compliance with ISO11607-1 and EN868-6.

Certification

SteriKraft G is produced at BillerudKorsnäs Skärblacka, which is certified in accordance with ISO 9001, ISO 14001, ISO 50001 and FSSC 22000.

Property	Unit				Method
Grammage	g/m ²		60	70	ISO 536
Tensile strength	kN/m	MD CD	6.9 4.1	8.0 4.8	ISO 1924-3
Tensile strength, wet	kN/m	MD	1.2	1.2	ISO 3781
Tear strength	mN	MD CD	440 500	540 620	ISO 1974
Burst strength	kPa		300	340	ISO 2758
Air resistance	s		47	47	ISO 5636-5
Porosity Bendtsen*	ml/min		255	255	ISO 5636-5*
Cobb 60s	g/m ²	MG	19	19	ISO 535
Surface roughness	ml/min	MG	90	100	ISO 8791-2
pH hot water extract			6	6	ISO 6588-2

*Calculated from Gurley measurements

MD = Machine Direction

CD = Cross Direction

MG = MG-side/RS = Reverse side

Test climate: 50% RH, 23C

The table shows typical values