

# Preliminary technical data sheet

Date: July 6, 2020

## Release 85 WHITE MG KRAFT PAPER

Production Unit: Skärblacka PM10

### End uses

Release 85 is an uncoated paper used as base for silicone coating.

#### Grammages

35 - 60 gsm

#### Materials

Release 85 is produced from pure, bleached pulp and consists entirely of primary fibers. These fibers are from slow growing Scandinavian forest, which gives the paper its inherent strength.

#### Silcone Systems

The paper can be coated with emulsion, solvent less and solvent silicone systems.

#### **Approvals**

Release 85 is produced in compliance with BfR and FDA food packaging norms.

#### Certification

Release 85 is produced at BillerudKorsnäs Skärblacka which is certified in accordance with ISO 9001, ISO 14001, ISO 50001 and FSSC 22000.

Release 85 is certified as compostable in accordance with ISO 18606:2013 and EN 13432 (09-2000).

Property	Unit								Method
Grammage	g/m <sup>2</sup>		35	40	45	48	50	60	ISO 536
Caliper	μm		44	49	54	58	60	68	ISO 534
Tensile strength	kN/m kN/m	MD CD	3.3 2.0	3.8 2.3	4.4 2.6	4.7 2.8	4.9 2.9	6.0 3.5	ISO 1924-3
Tear strength	mN mN	MD CD	180 200	210 240	240 290	260 310	275 330	340 415	ISO 1974
Air resistance	S		85	85	85	85	85	85	ISO 5636-5
Cobb 60s	g/m²	MG RS	22 22	22 22	22 22	22 22	22 22	22 22	ISO 535
Surface roughness	ml/min	MG RS	40 310	40 330	40 350	40 360	45 370	45 450	ISO 8791-2
ISO Brightness	%		84	84	84	84	84	84	ISO 2470
Moisture	%		5.8	5.8	5.8	5.8	5.8	5.8	Online QCS

MD = Machine Direction

CD = Cross Direction MG

MG = MG-side/RS = Reverse side Test climate:

Test climate: 50% RH, 23C

The table shows typical values

This specification is valid until 2021-07-06, or until a new specification has been sent to the customer.