

Technical data sheet

Date: January 01, 2018

QuickFill® White SE (F) WHITE SACK KRAFT PAPER

Production Unit: Karlsborg

End uses

QuickFill® White SE (F) is particularly suitable for applications involving fast filling of valve sacks, where friction, printability and appearance are also important. High porosity means that the sacks do not normally need to be perforated. QuickFill® White SE (F) is approved in accordance with the German norm for dangerous goods.

Grammages

 $70 - 90 \text{ g/m}^2$

Materials

QuickFill® White SE (F) is produced from pure, white kraft pulp and consists entirely of virgin fibre. The long and strong fibres, from the slow-growing forests of the Nordic region, give the paper its inherent strength.

Approvals

QuickFill® White SE (F) is produced in compliance with BfR and FDA for food contact.

Certification

Karlsborg mill is certified in accordance with ISO 9001, ISO 14001, ISO 50001, $\ensuremath{\mathsf{FSC}^{@}}$ CoC (FSC-C020000) and PEFC™ CoC (PEFC/05-33-136).

Other information

(F) means that the product is produced with an embossed pattern.

Property	Unit		Typical values	Typical values		
Grammage	g/m²		70	80	90	ISO 536
Tensile strength	kN/m kN/m	MD CD	4.9 3.5	5.6 4.0	6.3 4.5	ISO 1924-3
Tensile index	Nm/g Nm/g	MD CD	70 50	70 50	70 50	ISO 1924-3
Stretch	% %	MD CD	6.0 9.5	6.0 9.0	6.0 8.5	ISO 1924-3
TEA	J/m ² J/m ²	MD CD	180 225	210 250	235 270	ISO 1924-3
TEA Index	J/g J/g	MD CD	2.6 3.2	2.6 3.1	2.6 3.0	ISO 1924-3
TEA index geometric	J/g		2.9	2.8	2.8	
Tear strength	mN mN	MD CD	980 1080	1200 1320	1390 1490	ISO 1974
Tear index	mNm²/g mNm²/g	MD CD	14.0 15.5	15.0 16.5	15.5 16.5	ISO 1974
Brightness	%		85	85	85	ISO 2470
Cobb 60s	g/m²	WS	30	30	30	ISO 535
Air resistance	S		5	5	6	ISO 5636-5
Static friction coefficient			0.7	0.7	0.7	TAPPI T815
Moisture	%		7.5	7.5	7.5	ISO 287

MD = Machine Direction CD = Cross Direction

TS = Top side WS = Wire side (winded outside, recommended print side)

Test climate: 50% RH, 23°C